


MPH-95x 시리즈



Principal Characteristics

- Easy release
- High gloss
- Fine definition
- Good durability
- Processable with silicon or metal dies

Product Type

- MPH-950L
- MPH-950H
- MPH-950P

Metal Die Stamping Temperatures

• Up and down presses : 150 ~ 210 ℃

• Peripheral roll-on: 170 ~ 230 ℃

Specification

• Carrier film thickness : 12 μ m ~ 15 μ m

• Packaging: 640mm × 240m × 5rolls in a box

640mm × 120m × 10rolls in a box

Fields of Application

- PVC folders and book covers
- Cosmetics and pharmaceuticals containers
- Various plastic containers and caps
- Ballpoint pens and stationery
- OPP laminated paper

Suitable Plastics

- PVC, ABS, PS, SAN substrates
- PC, PP, PET, Acrylic substrates
- PE and various plastics

Silicon Rubber Die Stamping Temperatures

• Up and down presses: 170 ~ 210 °C

• Peripheral roll-on: 180 ~ 250 ℃

Health and Safety

• MSDS of the product is available on request.